

POLYLACTIC ACID POLYMER COMPOSITION AND ITS MOLDED ITEM

Publication number: JP9272790

Publication date: 1997-10-21

Inventor: MATSUI MASAO; KANAMORI
KENJI

Applicant: SHIMADZU CORP

Classification:

- international: *D01F6/62; B65D1/00; B65D1/09;
B65D65/02; C08J5/00; C08L67/00;
C08L101/16; D01F6/62; B65D1/00;
B65D1/09; B65D65/02; C08J5/00;
C08L67/00; C08L101/00; (IPC1-7):
C08L67/00; B65D1/09; B65D65/02;
C08J5/00; D01F6/62*

- European:

Application number: JP19960083751 19960405

Priority number(s): JP19960083751 19960405

[View INPADOC patent family](#)

[View list of citing documents](#)

[Report a data error here](#)

Abstract of JP9272790

PROBLEM TO BE SOLVED: To solve the problems that polylactic acid, when rapidly cooled in, e.g. injection molding, becomes amorphous and gives a molded item which is distorted by its own wt. at temps. between the glass transition point (about 60 deg.C) and the crystallization temp. (about 100 deg.C) and has a poor resistance to heat distortion and that polylactic acid has a high melt viscosity and hence its production or processing is difficult. SOLUTION: This polymer compsn. is a mixture comprising 97-40wt.% crystalline polyester polymer obtd. by the copolymn. of lactic acid as the main monomer and 1-30wt.% at least one comonomer selected from among X aliph. polyethers, maliph. polylactones, aliph. lactones aliph. polycarbonates, and their oligomers and 3-60wt.% polyester block copolymer comprising 97-50wt.% crystalline polyester segments formed from an aliph. dicarboxylic acid and a linear diol and 3-50wt.% polylactic acid segments.

Data supplied from the esp@cenet database - Worldwide